

SIGMAZINC 170

(DIMETCOTE 9)



6 pages

June 2009

DESCRIPTION

two component moisture curing zinc (ethyl) silicate coating

PRINCIPAL CHARACTERISTICS

- anticorrosive primer for structural steel
- high zinc content resulting in excellent corrosion protection
- complies with SSPC-Paint 20
- suitable as a system primer in various paint systems based on unsaponifiable binders
- galvanic action eliminates sub film corrosion
- good low temperature curing
- good impact and abrasion resistance
- must not be exposed to alkaline (more than pH 9) or acidic (less than pH 5.5) liquids

COLOURS AND GLOSS

grey - flat

BASIC DATA AT 20°C

(1 g/cm³ = 8.25 lb/US gal; 1 m²/l = 40.7 ft²/US gal)
 (data for mixed product)

Mass density

2.4 g/cm³

Volume solids

65 ± 2%

VOC (supplied)

max. 221 g/kg (Directive 1999/13/EC, SED)
 max. 480 g/l (approx. 4.0 lb/gal)

Recommended dry film thickness

- average dft 75 µm with a minimum of 60 µm on smooth non pitted, blast cleaned steel
- average dft 100 µm with a minimum of 75 µm on rough or pitted, blast cleaned steel

Theoretical spreading rate

8.7 m²/l for 75 µm *

Touch dry after

15 min. at 20°C

Overcoating interval

min. 16 hours *

max. unlimited, zinc salts must be removed

Curing time

12 hours *

(data for components)

Shelf life (cool and dry place)

binder: at least 9 months

pigment: at least 24 months (store pigment moisture free)

* see additional data

RECOMMENDED SUBSTRATE CONDITIONS AND TEMPERATURES

- **for immersion exposure:**
 - steel; blast cleaned to ISO-Sa2½, blasting profile 40 - 70 µm
 - steel with approved zinc silicate shop primer; sweep blasted to SPSS-Ss, welds, rusty and damaged areas blast cleaned to ISO-Sa2½
- **for atmospheric exposure conditions:**
 - steel; blast cleaned to ISO-Sa2½, blasting profile 40 - 70 µm
 - steel with approved zinc silicate shop primer; pretreated to SPSS-Pt3

SIGMAZINC 170

(DIMETCOTE 9)

June 2009

- weathered galvanised steel; blast cleaned to remove rust, to roughen the surface and to remove any zinc salts which might be present
- stainless steel; degreased and blast cleaned to roughness of 40 - 70 µm
- substrate temperatures from -5°C up to +50°C during application are acceptable
- substrate temperature should be at least 3°C above dew point
- relative humidity should be above 50%

INSTRUCTIONS FOR USE

mixing ratio by volume: binder to zinc powder 78 : 22

Many of Sigma's zinc silicates are supplied as 2 pack materials consisting of a jerrycan with pigmented binder and a drum containing a bag of zinc powder.

To ensure proper mixing of both components the instructions given below must be followed.

To avoid lumps in the paint do not add the binder to the zinc powder.

- 1) Take the bag with zinc powder out of the drum.
- 2.) Shake the binder in the jerrycan a few times to reach a certain degree of homogenisation.
- 3.) Pour about 2/3 of the binder in the empty drum.
- 4.) With the jerrycan now reduced in weight and containing more free space, shake it vigorously to obtain a homogeneous mix with no deposits left on the bottom, and add this to the drum.
- 5.) Add the zinc powder gradually to the pigmented binder in the drum and at the same time continuously stir the mixture by using a mechanical mixer (keep the speed low).
- 6.) Stir the zinc dust powder thoroughly through the binder (high speed) and keep stirring till, a homogeneous mixture is obtained.
- 7.) Strain mixture through a 30 - 60 mesh screen.
- 8.) Agitate continuously during application (low speed).
The use of a dedicated pump with a constant agitation for a zinc silicate coating is recommended.

Note: At application temperature above 30°C addition of max 10% by volume of Thinner 90-53 may be necessary.

| | |
|----------------|-----------------------|
| Induction time | none |
| Pot life | 8 hours at 20°C * |
| | * see additional data |

AIRLESS SPRAY

| | |
|---------------------|--|
| Recommended thinner | Thinner 90-53 |
| Volume of thinner | 0 - 10%, depending on required thickness and application conditions |
| Nozzle orifice | approx. 0.48 - 0.64 mm (= 0.019 - 0.025 in) |
| Nozzle pressure | 9 - 12 MPa (= approx. 90 - 120 bar; 1280 - 1700 p.s.i.) a dedicated pump for a zinc silicate coating with constant agitation must be used |

SIGMAZINC 170
(DIMETCOTE 9)

June 2009

AIR SPRAY

Recommended thinner Thinner 90-53
 Volume of thinner 0 - 10%, depending on required thickness and application conditions
 Nozzle orifice 2 mm
 Nozzle pressure 0.3 MPa (= approx. 3 bar; 43 p.s.i.)
 a dedicated pump for a zinc silicate coating with constant agitation must be used

BRUSH

only for touch up and spot repair
 Recommended thinner Thinner 90-53
 Volume of thinner 5 - 15%
 apply a visible wet coat with a max. dft of 25 µm
 same for subsequent coats in order to obtain the required dft

CLEANING SOLVENT

Thinner 90-53

UPGRADING DFT

only valid for spray application
 if the dft is below specification and an extra coat of SigmaZinc 170 has to be applied, SigmaZinc 170 should be thinned down with 25 - 50% Thinner 90-53, in order to obtain a visible wet coat that remains wet for some time

SAFETY PRECAUTIONS

for paint and recommended thinners see safety sheets 1430, 1431 and relevant material safety data sheets
 this is a solvent borne paint and care should be taken to avoid inhalation of spray mist or vapour as well as contact between the wet paint and exposed skin or eyes

ADDITIONAL DATA

highly pigmented zinc silicate primers produce dry films with void spaces in between the particles

Film thickness and spreading rate

| | | | |
|--|-----|-----|-----|
| theoretical spreading rate m ² /l | 8.7 | 6.5 | 5.2 |
| dft in µm | 75 | 100 | 125 |

above 150 µm dft mudcracking can occur
 max. dft when brushing:

35 µm

SIGMAZINC 170
(DIMETCOTE 9)

June 2009

Overcoating table for 50% RH minimum

| | | | | | | |
|-----------------------|--|----------|----------|----------|----------|----------|
| substrate temperature | -5°C | 0°C | 10°C | 20°C | 30°C | 40°C |
| minimum interval | 48 hours | 48 hours | 48 hours | 32 hours | 24 hours | 12 hours |
| maximum interval | unlimited, provided the surface is cleaned from contamination and zinc salts | | | | | |

Overcoating table for 70% RH and higher

| | | | | | | |
|-----------------------|--|----------|----------|----------|----------|---------|
| substrate temperature | -5°C | 0°C | 10°C | 20°C | 30°C * | 0°C |
| minimum interval | 24 hours | 24 hours | 24 hours | 16 hours | 12 hours | 6 hours |
| maximum interval | unlimited, provided the surface is cleaned from contamination and zinc salts | | | | | |

- a RH below 50% requires a much longer overcoating time
- if part of a coating system and in order to avoid possible popping effects (pinholes) SigmaZinc 170 should be sealed with approved coatings
- SigmaZinc 170 is a moisture curing zinc silicate, this means that it only cures after sufficient take up of water from the atmosphere during and after application; it is recommended that relative humidity and temperature are measured during the curing time
- before entering service or overcoating, a sufficient degree of cure should be obtained
- when curing conditions are unfavourable or when reduced overcoat times are desired, curing can be accelerated 4 hours after application by:
 - wetting or soaking with water, keeping the surface wet for the next 2 hours, followed by drying
 - wetting or soaking with a 0.5% ammonia solution, followed by drying
- before overcoating with topcoats, SigmaZinc 170 should always be visibly dry and checked on sufficient curing
- for measuring of the curing, the MEK rub test according to ASTM 4752 is a suitable method: after 50 double rubs with a cloth soaked in MEK (or alternatively Thinner 90-53) no dissolving of the coating should be observed

SIGMAZINC 170
(DIMETCOTE 9)

June 2009

Curing table for 50% RH and higher

| substrate temperature | dry to handle | full cure |
|-----------------------|---------------|-----------|
| -5°C | 2 hours | 24 hours |
| 0°C | 2 hours | 24 hours |
| 10°C | 1 hour | 18 hours |
| 20°C | 30 min. | 12 hours |
| 30°C | 30 min. | 6 hours |
| 40°C | 30 min. | 4 hours |

- SigmaZinc 170 is a moisture curing zinc silicate, this means that it only cures after sufficient take up of water from the atmosphere during and after application; it is recommended that relative humidity and temperature are measured during the curing time
- relative humidity during curing recommended to be above 50%
- adequate ventilation must be maintained during application and curing (please refer to sheets 1433 and 1434)

Pot life (at application viscosity)

| | |
|------|----------|
| 0°C | 16 hours |
| 10°C | 12 hours |
| 20°C | 8 hours |
| 30°C | 4 hours |

Worldwide availability

Whilst it is always the aim of PPG Protective & Marine Coatings to supply the same product on a worldwide basis, slight modification of the product is sometimes necessary to comply with local or national rules/circumstances. Under these circumstances an alternative product data sheet is used.

REFERENCES

| | |
|---|----------------------------|
| Explanation to product data sheets | see information sheet 1411 |
| Safety indications | see information sheet 1430 |
| Safety in confined spaces and health safety | |
| Explosion hazard - toxic hazard | see information sheet 1431 |
| Safe working in confined spaces | see information sheet 1433 |
| Directives for ventilation practice | see information sheet 1434 |
| Cleaning of steel and removal of rust | see information sheet 1490 |
| Relative humidity - substrate temperature - air temperature | see information sheet 1650 |

SIGMAZINC 170

(DIMETCOTE 9)

June 2009

LIMITATION OF LIABILITY

The information in this data sheet is based upon laboratory tests we believe to be accurate and is intended for guidance only. All recommendations or suggestions relating to the use of the Sigma Coatings products made by PPG Protective & Marine Coatings, whether in technical documentation, or in response to a specific enquiry, or otherwise, are based on data which to the best of our knowledge are reliable. The products and information are designed for users having the requisite knowledge and industrial skills and it is the end-user's responsibility to determine the suitability of the product for its intended use.

PPG Protective & Marine Coatings has no control over either the quality or condition of the substrate, or the many factors affecting the use and application of the product. PPG Protective & Marine Coatings does therefore not accept any liability arising from loss, injury or damage resulting from such use or the contents of this data sheet (unless there are written agreements stating otherwise).

The data contained herein are liable to modification as a result of practical experience and continuous product development.

This data sheet replaces and annuls all previous issues and it is therefore the user's responsibility to ensure that this sheet is current prior to using the product.

The English text of this document shall prevail over any translation thereof.

PDS

7570