

Smith & Allan Valley Street North Darlington Co Durham DL1 1QE



01325 462228



01325 368122



enquiries@smithandallan.com



www.smithandallan.com

# Product Information: Absolute LT 2 Grease

### **Description**

Absolute LT 2 is premium performance multi-application grease formulated using severely hydrocracked base oils and a superior quality calcium sulphonate complex thickener system. The product offers long life even at elevated temperatures providing long lasting equipment protection, as well as exhibiting excellent water resistance. The high mechanical stability of the product and it's resistance to breakdown reduces bearing wear even when under heavy load conditions. The product also displays outstanding oxidation stability and rust protection.

### **Applications**

Absolute LT 2 is suitable for use in a range of industrial and automotive applications including; general manufacturing, fleet, power generation, off-highway and forestry. It is particularly recommended for high temperature and long life applications which include equipment running continuously at temperatures up to 200°C; wheel bearings and automotive chassis; sealed for life bearings; constant velocity joints and ovens & kilns.

#### Performance Features

Long lasting at high temperatures Superior water washout resistance

High mechanical stability

Highly resistant to oxidation

Maintains consistency

**Excellent load carrying ability** 

Outstanding rust protection

Multi-application product

## Typical Data

Characteristic

**NLGI Grade** 

Colour

Appearance

Worked Penetration

Flash Point

Drop Point

Water Washout @ 79°C

Oxidisation @ 100 hrs, psi drop

Copper Corrosion

Four Ball Weld Point

Temperature Range

# Performance Level

NLGI Standard: GC-LB

Result

2

Burgundy

**Smooth Grease** 

284

240°C

314°C

1.5%

2.2

1b

500 kg

-20°C to +200°C

Figures based on average production values O









Issue 1 November 2017

The above information is supplied to the best of our knowledge and belief on the basis of current industry and our own development work. Subject to amendment